

Leader Clipperlon 2120

Modified PTFE Gaskets

DESCRIPTION

Modified PTFE gasket material containing biaxial-oriented chains to obtain a tight seal for demanding applications. Clipperlon 2120 is a very dense material with low compressibility, high recovery, and low creep properties. Off-White in color and produced with modified PTFE and barium sulfate filler.

APPLICATION

Particularly suitable for use with hydrofluoric acid and a wide variety of different media across the whole pH range. Applications can be found in chemical, pharmaceutical, food and beverage, and general industry. Due to the high density, this material is highly recommended for applications with monomers to avoid the 'popcorning' effect. This effect will result when the monomer enters the microvoids of the PTFE.

CHEMICAL COMPATIBILITY

Particularly suitable for use with hydrofluoric acid but not pure hydrogen fluoride. Best for use with strong alkalis, solvents, fuels, water, steam, and chlorine. Other applications include solvents, fuels, water, oil, chlorine, and caustics. A chemical resistance list is available upon request. Pressure up to 1200 psi. Temperature from -450°F up to 500°F.

AVAILABLE OPTIONS

Flange gaskets and sheets are available in thickness of 1/32", 1/16", and 1/8". Other thicknesses available on request. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings or by given sizes.

APPROVALS & CERTIFICATES

- FDA 21 CFR 177.1550
- TA-Luft
- EC1935 (10/2011)
- The Chlorine Institute / Pamphlet 95

SEALING CHARACTERISTICS

- Significant reduced creep (non-cold flow)
- Low leak rate
- Good electrical insulation properties
- Outstanding chemical resistance
- Non-aging
- Excellent sealability for low-torque applications

TECHNICAL DATA	
Maximum Temperature [°F]	500
Maximum Pressure [PSI]	1200
Density [g/cm ³]	2.8
Leakage Specific Leak Rate [DIN 28090-2] [mg/(s*m)]	0.01
Minimum Initial Stress [DIN E 2505 part 2] [N/mm ²]	20
Maximum Initial Stress [DIN E 2505 part 2] [N/mm ²]	150
M-Value	3.5
Y- Value [psi]	2450
ASTM F36 Recovery [% min]	40
Gasket Required Flange Roughness [Ra micron]	3.2-6.3
Gasket Required Flange Roughness [RMS]	125-250

All information contained on this datasheet is subject to change without prior notice. LEADER GASKET TECHNOLOGIES AND ITS AFFILIATES MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE. Buyer/end-user is responsible for determining whether the product is fit for a particular purpose and suitable for buyer's/user's method of use or application. Failure to follow procedures for selection, installation, care, maintenance, and storage of gaskets and other sealing products may result in the product's failure to perform properly and may result in damage to property and/or serious injury. Goodall and its affiliates shall not be subject to, and they hereby disclaim, any obligations or liabilities (including but not limited to all consequential, incidental, and contingent damages) arising from tort claims (including without limitation negligence and strict liability) or other theories of law.

TECHNICAL DATA	
Max Seating Stress [Qsmax bei RT EN13555] [n/mm2]	100
Tensile Strength (quer) DIN 52910 [N/mm]	>=(13) 1885
Advice Seating Stress at Assembly [psi]	5000
ROTT [Gb]	432
ROTT [a]	0.318
ROTT [Gs]	0.964
Compressibility, [ASTM F36], [%]	4-8
ASTM F37 Sealability [ml/min] Sg=1000 psi=30	0.22
ASTM F38 Creep Relaxation [%]	12
ASTM F152 Average Tensile [psi]	2000