

Leader Style 961

Rubberbonded Fiber Jointing Sheets

DESCRIPTION

White in color and manufactured using SBR/Aramid Fiber.

APPLICATION

Steam, water, air gases, mild solvents and alkalis.

CHEMICAL COMPATIBILITY

See link: LGT Chemical Compatibility Chart

DELIVERY OPTIONS

Standard stock sheet sizes are available in 60" x 60", 60" x 120". Standard stock sheet thicknesses available are 1/64", 1/32", 1/16", and 1/8" (special thicknesses are available upon request)

TEMPERATURE

Max. Intermittent Temperature Rating: 700 F
Max. Continuous Temperature Rating: 400 F

TECHNICAL DATA

max Temperature [°F]	400
Max Temp. Limit [°F]	700
Max Contin. Temp. Limit [F]	400
Min. Temp. [°F]	-75
max Pressure [psi]	1000
density [g/cm3]	1.2
M-Value	5.5
Y- Value [psi]	3600
ASTM F36 Recovery [% min]	40
Gasket required flange roughness [Ra micron]	3,2-6,3
Gasket required flange roughness [RMS]	125-250
Tensile Strength (quer) DIN 52910 [N/mm]	>11
Advice Seating stress at assembly [psi]	4000
Max Pressure Rating [psi]	1000
Max P x T	250000
compressability, [ASTM F36], [%]	15 - 35
ASTM F37 Sealability [ml/min] Sg=1000 psi=30	no data
BS 7531 Gas Leakage [ml/min]	<1.0
ASTM F38 Creep Relaxation [%]	32
BS 7531 Residual Stress [mpa]	16
ASTM F152 Average Tensile [psi]	2000
ASTM F146 Fuel B @ 70-85 F Thick. Increase [%]	15 - 35
IRM 903 @ 300 oF Thickness Increase [%]	15 - 35
ASTM Fuel B @ 70-85 oF Weight Increase [%]	20 max.
Rubber Binder	SBR

LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Purnovicka cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895